

Product Texts

Polycaprolactone copolyester-based TPU.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	47	MPa	ISO 527
Stress at 100% elongation	8	MPa	ISO 527
Stress at 300% elongation	17	MPa	ISO 527
Strain at break TPE	511	%	ISO 527
Compression set at 70 °C, 24h	19	%	ISO 815
Tear strength	125^[1]	kN/m	ISO 34-1
Abrasion resistance	20	mm ³	ISO 4649
Shore A hardness	92	-	ISO 7619-1
Shore D hardness	46	-	ISO 7619-1
ASTM Data			
Compression Set , 22 hr @ 158 °F	23	%	ASTM D 395

1: Nicked

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, A	133	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1150	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	2	h	-
Processing humidity	≤0.02	%	-
Feed temperature	40	°C	-
Zone 1	185	°C	-
Zone 2	190	°C	-
Zone 3	190	°C	-
Zone 4	195	°C	-
Nozzle temperature	195	°C	-

Characteristics

Processing

Injection Molding

Features

Copolymer

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe