

POLYPUR® CB 1110

TPU

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.9	mm/mm	ASTM D 955
Mold Shrinkage, TD	1.4	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	835	MPa	ASTM D 790
Shore D Hardness	76	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Coefficient of Thermal Expansion, TD	150	E-6/K	ASTM D 696

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America