

POLYPUR® FPU 1185

TPU

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	85	-	ASTM D 2240
Compression Set , 22 hr @ 73 °F	16	%	ASTM D 395
Compression Set , 22 hr @ 158 °F	65	%	ASTM D 395

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America