

POLYPUR® FPU 1387ZB

TPU

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Elongation at Break	25	%	ASTM D 638
Flexural Modulus	1498	MPa	ASTM D 790
Izod Impact notched, 1/8 in	181	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1150	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America