

**4TECH 9T22130 H**

TPU-GF30

4Plas

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2250</b>	MPa	ISO 527
Stress at break	<b>70</b>	MPa	ISO 527
Strain at break	<b>15</b>	%	ISO 527
Izod notched impact strength, +23°C	<b>40</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>25</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>-30</b>	°C	-

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>125</b>	°C	ISO 75-1/-2

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1450</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

Europe