

RTP 1207 S-65D

TPU-GF40

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2758	MPa	ASTM D 638
Tensile Strength	82.7	MPa	ASTM D 638
Flexural Modulus	2758	MPa	ASTM D 790
Flexural Strength	82.7	MPa	ASTM D 790
Shore D Hardness	75	-	ASTM D 2240
Izod Impact notched, 1/8 in	374	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1540	kg/m ³	ASTM D 792
Moisture Content	0.02	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	82.2	°C	-
Pre-drying - Time	6	h	-
Melt temperature	193 - 216	°C	-
Mold temperature	15.6 - 32.2	°C	-
Injection pressure	48.3 - 82.7	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific