

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	40	MPa	ASTM D 638
Flexural Modulus	1207	MPa	ASTM D 790
Flexural Strength	47	MPa	ASTM D 790
Shore D Hardness	68	-	ASTM D 2240
Izod Impact notched, 1/8 in	694	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	294	J/m	ASTM D 256
Temperature	-40	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	95	°C	ASTM D 648
DTUL @ 264 psi	61	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1310	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets