

Tecothane® TT-2074A-B40

TPU-Z40

The Lubrizol Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.01	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	19.31	MPa	ASTM D 790
Shore A Hardness	83	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1570	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Applications

Medical

Chemical Resistance

General Chemical Resistance, Radiation Resistance

Regional Availability

North America, Europe, Asia Pacific