

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	25	MPa	ISO 37
Strain at break	550	%	ISO 37
Tear strength	55	kN/m	ISO 34-1
Abrasion resistance	40	mm ³	ISO 4649
Shore A hardness	80	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	205 - 225	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, South and Central America

Delivery form

Natural Color