

Volaprint TPU 70 Transparent

TPU

Volaprint 3 de-store

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	30	MPa	ISO 527
Stress at break TPE	45	MPa	ISO 527
Strain at break TPE	850	%	ISO 527

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ISO 1183

Characteristics

Processing

Additive Manufacturing

Chemical Resistance

Grease Resistance, Oil Resistance

Delivery form

Monofilament

Regional Availability

Europe

Special Characteristics

Transparent