

WANTHANE® WHT-1580

TPU

Wanhua Chemical Group Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	4	MPa	ASTM D 412
Modulus at 300% Elongation	8	MPa	ASTM D 412
Shore A Hardness	80	-	ASTM D 2240
Tear Strength	80	kN/m	ASTM D 624
Tensile Strength	26	MPa	ASTM D 412
Elongation at Break	650	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa