

**WANTHANE® WHT-1680AB**

TPU

Wanhua Chemical Group Co., Ltd.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Abrasion resistance	<b>92</b>	mm <sup>3</sup>	ISO 4649
<b>ASTM Data</b>			
Modulus at 100% Elongation	<b>5</b>	MPa	ASTM D 412
Modulus at 300% Elongation	<b>9</b>	MPa	ASTM D 412
Shore A Hardness	<b>80</b>	-	ASTM D 2240
Tear Strength	<b>80</b>	kN/m	ASTM D 624
Tensile Strength	<b>30</b>	MPa	ASTM D 412
Elongation at Break	<b>710</b>	%	ASTM D 412

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1190</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Film Extrusion, Sheet Extrusion, Other Extrusion, Coating, Blow Molding

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Sports Equipment

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa