

WANTHANE® WHT-2185

TPU

Wanhua Chemical Group Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	6	MPa	ASTM D 412
Modulus at 300% Elongation	9	MPa	ASTM D 412
Shore A Hardness	85	-	ASTM D 2240
Tear Strength	110	kN/m	ASTM D 624
Tensile Strength	26	MPa	ASTM D 412
Elongation at Break	520	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Certifications

Food contact, Food approval FDA 21 CFR

Chemical Resistance

Hydrolytically Stable, Oil Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa