

WANTHANE® WHT-7185

TPU

Wanhua Chemical Group Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	8	MPa	ASTM D 412
Modulus at 300% Elongation	23	MPa	ASTM D 412
Shore A Hardness	85	-	ASTM D 2240
Tear Strength	100	kN/m	ASTM D 624
Tensile Strength	35	MPa	ASTM D 412
Elongation at Break	350	%	ASTM D 412
Other properties			
Density	1220	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Film Extrusion, Sheet Extrusion, Wire/Cable Extrusion, Other Extrusion, Coating, Calandring

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Fungus Resistance

Chemical Resistance

General Chemical Resistance, Hydrolytically Stable

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa