

WANTHANE® WHT-8290

TPU

Wanhua Chemical Group Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	9	MPa	ASTM D 412
Modulus at 300% Elongation	15	MPa	ASTM D 412
Shore A Hardness	90	-	ASTM D 2240
Tear Strength	100	kN/m	ASTM D 624
Tensile Strength	28	MPa	ASTM D 412
Elongation at Break	400	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Glass Transition Temperature	-42	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1120	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Special Characteristics

U.V. stabilized or stable to weather, Transparent

Features

Fungus Resistance

Chemical Resistance

Hydrolytically Stable

Certifications

Food contact, Food approval FDA 21 CFR, US Pharmacopeia Class VI Approved

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa