

FORPRENE® 6NM001A85 NEUTRO

TPV

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
[C] Stress at 100% elongation	4.6	MPa	ISO 527
[C] Stress at 300% elongation	6	MPa	ISO 527
[C] Compression set at 70 °C, 24h	46	%	ISO 815
[C] Compression set at 100 °C, 24h	56	%	ISO 815

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Density	934	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Delivery form**

Natural Color