

FORPRENE® 6SD001A55 NEUTRO

TPV

Celanese

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Stress at 100% elongation | 1.5 | MPa | ISO 527 |
| ^[C] Stress at 300% elongation | 2.7 | MPa | ISO 527 |
| ^[C] Compression set at 70 °C, 24h | 29 | % | ISO 815 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| ^[C] Density | 923 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color