

FORPRENE® 6SD901A90 NERO

TPV

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	4.8	MPa	ISO 527
^[C] Stress at 300% elongation	6.3	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	56	%	ISO 815

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	932	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Black