

SANTOPRENE® 101-80

TPV

Celanese

Other properties	Value	Unit	Test Standard
^[C] Density	960	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Profile Extrusion, Sheet Extrusion, Blow Molding, Thermoforming

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Delivery form

Pellets