

Product Texts

Experimental Polyethylene Resin.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.32	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	20.6	MPa	ASTM D 638
Izod Impact notched, 1/8 in	100	J/m	ASTM D 256

Other properties

	Value	Unit	Test Standard
Density	958	kg/m ³	ASTM D 792

Characteristics

Certifications

Recycled Resin Content, Post-Consumer Recyclate

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa