

PETILEN YY I 668 (UV)
(PE-HD)

Petkim Petrokimya A.S.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5.45	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	28.9	MPa	ASTM D 638
Tensile Strength at Break	23.5	MPa	ASTM D 638
Elongation at Break	1250	%	ASTM D 638
Izod Impact notched, 1/8 in	49	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	968	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Chemical Resistance

Environmental Stress Crack Resistance