

PETILEN YY S 0464

(PE-HD)

Petkim Petrokimya A.S.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.35	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26.5	MPa	ASTM D 638
Tensile Strength at Break	36.8	MPa	ASTM D 638
Elongation at Break	1110	%	ASTM D 638
Izod Impact notched, 1/8 in	589	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	964	kg/m ³	ASTM D 792

Characteristics**Processing**

Blow Molding

Regional Availability

Europe

Chemical Resistance

Environmental Stress Crack Resistance