

**Product Texts**

5% glass fibre reinforced ABS-PC blend with increased heat resistance

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	17	cm <sup>3</sup> /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	3200	MPa	ISO 527
<sup>[C]</sup> Stress at break	67	MPa	ISO 527
<sup>[C]</sup> Strain at break	4	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	45	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	35	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	15	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	12	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	115	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	130	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	128	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	>1E15	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1160	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	3 - 6	h	-
Melt temperature	240 - 280	°C	-
Mold temperature	40 - 80	°C	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Platable

**Delivery form**

Granules

**Regional Availability**North America, Europe, Asia Pacific, South and Central America,  
Near East/Africa**Additives**

Release agent

**Other text information****Injection molding**PREPROCESSING; **Pretreatment**

Predrying: 3-6h / 80°C

**PROCESSING ;Processing:**

Melttemperature	240 - 280	°C
Mouldtemperature	40 - 80	°C