

**AUROblend® PC+PET HI black 9005**

(PC+PET)

Aurora Kunststoffe GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	20	cm <sup>3</sup> /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2050	MPa	ISO 527
Yield stress	45	MPa	ISO 527
Strain at break	>50	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	45	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	25	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	250	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	90	°C	ISO 75-1/-2
Vicat softening temperature, B	130	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

Other properties	Value	Unit	Test Standard
Water absorption	0.75	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1200	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	110	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.01	%	-
Melt temperature	270	°C	-
Mold temperature	80	°C	-

**Characteristics****Processing**

Injection Molding

**Applications**

Automotive

**Delivery form**

Black

**Regional Availability**

Europe