

**CFB5130N-BK1**

(PC+ABS)

Pontex Polyblend Co., Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>8</b>	g/10min	ASTM D 1238

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>49</b>	MPa	ASTM D 638
Flexural Modulus	<b>2060</b>	MPa	ASTM D 790
Flexural Strength	<b>73.6</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>392</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>95</b>	°C	ASTM D 648

**Characteristics****Regional Availability**

Asia Pacific