

## HDPE caps regrind

(PE-HD+PP+PET)

Iterum

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>Other Standards<sup>[S]</sup></b>			
Melt flow index, MFI	3	g/10min	-
Temperature	190	°C	-
Load	2.16	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

Thermal properties	Value	Unit	Test Standard
<b>Other Standards<sup>[S]</sup></b>			
Melting temperature, 10°C/min	133	°C	-

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Moisture Content	2	%	-
Bulk density	325	kg/m <sup>3</sup>	-

### Characteristics

#### Certifications

Recycled Resin Content, Post-Industrial Recyclate

#### Regional Availability

Europe