

HIPTEN® 21015

(PE-LD)

HIP-Petrohemija

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.5	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	10	MPa	ISO 527
Stress at break	14	MPa	ISO 527
Shore D hardness	44	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	921	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Applications

General Purpose

Regional Availability

Europe