

**Product Texts**

Heat Stabilized, Lubricated

ISO 1043 PA46

Stanyl® TW341-B is a non-reinforced high heat polyamide that offers excellent wear & friction properties in combination with outstanding creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle-time advantages and excellent flow.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Density of melt	990	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.25	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	2670	J/(kg K)	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	3300 / 1000	MPa	ISO 527
<sup>[C]</sup> Yield stress	100 / 55	MPa	ISO 527
<sup>[C]</sup> Yield strain	10 / 20	%	ISO 527
<sup>[C]</sup> Nominal strain at break	30 / >50	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1000h	* / 550	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	9 / 35	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	4 / 4	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	295 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	75 / *	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	190 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	280 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	290 / *	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	85 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	110 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Oxygen index	27 / *	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	1E12 / 1E7	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	20 / 10	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	350 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	13.5 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	3.7 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1180 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Viscosity number	185 / *	cm³/g	ISO 307, 1157, 1628
[C]: CAMPUS			

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Platable, Heat stabilized or stable to heat

**Delivery form**

Pellets

**Regional Availability**

North America, Europe, Asia Pacific

**Additives**

Lubricants, Release agent

**Other text information**

**Injection molding**

[Injection Molding Recommendations](#)

[Hot runner recommendations for molding high heat performance Engineering Materials](#)

[Steel recommendations for molds screws and barrels](#)

[Supporting document for Stanyl quality processing](#)

[Trouble shooting guideline for injection molding](#)