

PETILEN F2-21T

(PE-LD)

Petkim Petrokimya A.S.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 2.5 | g/10min | ASTM D 1238 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |

| Optical properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Gloss | 66 | - | ASTM D 2457 |
| Haze | 7 | % | ASTM D 1003 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 921 | kg/m ³ | ASTM D 792 |

Characteristics**Applications**

Packaging

Regional Availability

Europe