

PETILEN F5-21T

(PE-LD)

Petkim Petrokimya A.S.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4.75	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Optical properties	Value	Unit	Test Standard
ASTM Data			
Gloss	70	-	ASTM D 2457
Haze	6.9	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	921	kg/m ³	ASTM D 792

Characteristics**Applications**

Packaging

Regional Availability

Europe