

PETILEN G03-5

(PE-LD)

Petkim Petrokimya A.S.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.3	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Optical properties	Value	Unit	Test Standard
ASTM Data			
Gloss	57	-	ASTM D 2457
Haze	9.3	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	921	kg/m ³	ASTM D 792

Characteristics**Processing**

Film Extrusion, Blow Molding

Regional Availability

Europe

Applications

Building Construction, Packaging