

**PETILEN G08-21T**

(PE-LD)

Petkim Petrokimya A.S.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>0.875</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Optical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Gloss	<b>58</b>	-	ASTM D 2457
Haze	<b>8.8</b>	%	ASTM D 1003

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>921</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Regional Availability**

Europe