

PETILEN H2-21T

(PE-LD)

Petkim Petrokimya A.S.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Optical properties	Value	Unit	Test Standard
ASTM Data			
Gloss	66	-	ASTM D 2457
Haze	6.6	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	921	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

Europe