

PETILEN I22-19T

(PE-LD)

Petkim Petrokimya A.S.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	23	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Other properties			
Density	919	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

Europe