

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	922	kg/m ³	ASTM D 792

Film Properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break, MD	40	MPa	ASTM D 882
Tensile Strength at Break, TD	20	MPa	ASTM D 882
Elongation at Break, MD	750	%	ASTM D 882
Elongation at Break, TD	800	%	ASTM D 882
Type of extrusion	blown	-	-
Thickness of specimen	0.03	mm	-

Characteristics

Processing

Blown Film Extrusion

Delivery form

Pellets

Additives

Antiblocking agent

Special Characteristics

High impact or impact modified

Features

Low Odor, Copolymer, Butene Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

Asia Pacific