

Product Texts

Lumicene mPE M 2711 PCE is a metallocene based Linear Low Density Polyethylene with hexene as comonomer.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.2	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties

	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	119	°C	ISO 11357-1/-3

Optical properties

	Value	Unit	Test Standard
ISO Data			
Haze	8	-	ISO 14782
ASTM Data			
Gloss	65	-	ASTM D 2457

Other properties

	Value	Unit	Test Standard
Density	927	kg/m ³	ISO 1183

Film Properties

	Value	Unit	Test Standard
ISO Data			
Stress at yield, parallel	13.5	MPa	ISO 527-3
Stress at yield, normal	14	MPa	ISO 527-3
Stress at break, parallel	51	MPa	ISO 527-3
Stress at break, normal	48	MPa	ISO 527-3
Maximum strain, parallel	650	%	ISO 527-3
Maximum strain, normal	720	%	ISO 527-3
Dart drop A	230	g	ISO 7765-1
Type of extrusion	blown	-	-
Thickness of specimen	0.04	mm	-

Processing Recommendation Extrusion

	Value	Unit	Test Standard
Type of extrusion	blown	-	-
Melt temperature	180 - 230	°C	-

Characteristics

Processing

Blown Film Extrusion, Film Extrusion

Additives

Antiblocking agent

Features

Blending Resin, Tribological Grade

Chemical Resistance

Oxidation Resistance

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe