

Petrothene GA503028

(PE-LLD)

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.5	g/10min	ASTM D 1238
Optical properties			
ASTM Data			
Gloss	25	-	ASTM D 2457
Haze	30	%	ASTM D 1003
Other properties			
ASTM Data			
Density	925	kg/m ³	ASTM D 792
Film Properties			
ASTM Data			
Tensile Strength at Break, MD	33.1	MPa	ASTM D 882
Tensile Strength at Break, TD	23.4	MPa	ASTM D 882
Elongation at Break, MD	690	%	ASTM D 882
Elongation at Break, TD	740	%	ASTM D 882
Type of extrusion	blown	-	-
Thickness of specimen	0.038	mm	-

Characteristics**Processing**

Blown Film Extrusion, Film Extrusion

Additives

Antiblocking agent

Features

Blending Resin, Good Drawdown, Copolymer, Butene Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America