

Petrothene GA601030

(PE-LLD)

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Vicat Temperature	105	°C	ASTM D 1525
Optical properties			
ASTM Data			
Gloss	35	-	ASTM D 2457
Haze	22	%	ASTM D 1003
Other properties			
Density	918	kg/m ³	ASTM D 792
Film Properties			
ASTM Data			
Tensile Strength at Break, MD	55.8	MPa	ASTM D 882
Tensile Strength at Break, TD	42.1	MPa	ASTM D 882
Elongation at Break, MD	580	%	ASTM D 882
Elongation at Break, TD	700	%	ASTM D 882
Thickness of specimen	0.025	mm	-

Characteristics**Processing**

Film Extrusion

Delivery form

Pellets

Additives

Antiblocking agent

Features

Good Drawdown, Heat Sealable

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America