

LATILUB 88/50-20T

(PEEK+PTFE)

LATI Industria Termoplastici S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	3900	MPa	ISO 527
Yield strain	7	%	ISO 527
Stress at break	75	MPa	ISO 527
Strain at break	30	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	155	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	190	°C	ISO 75-1/-2
Vicat softening temperature, B	270	°C	ISO 306
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-
Glow Wire Ignition Temperature (GWIT)	875	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
ASTM Data			
UL 94 Flame rating	V-1	-	UL 94
Thickness tested	0.75	mm	-
Limiting Oxygen Index	35	%	ASTM D 2863
Electrical properties			
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257
Other properties			
Density	1400	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	3	h	-
Melt temperature	360 - 390	°C	-
Mold temperature	170 - 200	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Additives

Lubricants