

VICTREX® PEEK 150FW30

(PEEK+PTFE)-CF30

Victrex plc

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	16000	MPa	ISO 527
Stress at break	200	MPa	ISO 527
Strain at break	1.8	%	ISO 527
Flexural modulus, 23°C	14000	MPa	ISO 178
Flexural strength	280	MPa	ISO 178
Charpy impact strength, +23°C	35	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	35	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	6.5	kJ/m ²	ISO 180/1A
Shore D hardness	84.5	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	143	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	325	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	9	E-6/K	ISO 11359-1/-2

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	100000	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Water absorption	0.3	%	Sim. to ISO 62
Density	1430	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	3 - 5	h	-
Processing humidity	≤0.02	%	-
Mold temperature	170 - 200	°C	-
Feed temperature	≤100	°C	-
Zone 1	365	°C	-
Zone 2	370	°C	-
Zone 3	375	°C	-
Zone 4	380	°C	-
Nozzle temperature	385	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Features

Tribologic Grade

Chemical Resistance

General Chemical Resistance

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa