

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	0.9	g/10min	ISO 1133
Temperature	190	°C	-
Load	5	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	700	MPa	ISO 527
Yield stress	18	MPa	ISO 527
Strain at break	350	%	ISO 527
<b>Thermal properties</b>			
<b>ISO Data</b>			
Vicat softening temperature, A	116	°C	ISO 306
<b>Other properties</b>			
Density	943	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Pipe/Tube Extrusion, Other Extrusion

#### Certifications

Drinking water contact

#### Features

Copolymer

#### Regional Availability

Europe