

**GUR® 5523**

(PE-UHMW)

Celanese

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Vicat softening temperature, B	80	°C	ISO 306

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	930	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Delivery form**

Pellets, Granules

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa