

Polimaxx H610B
(PE-UHMW)

IRPC

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	132	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	940	kg/m ³	ISO 1183
Intrinsic Viscosity	5.2	dl/g	-
Bulk density	380	kg/m ³	-

Characteristics

Delivery form

Powder

Certifications

RoHS compliant

Special Characteristics

High impact or impact modified

Applications

Electrical and Electronical

Chemical Resistance

General Chemical Resistance

Regional Availability

Europe, Asia Pacific