

**DURACON® AW-01LV**

(POM+PE)

Polyplastics

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>8</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
Melt flow index, MFI	<b>9</b>	g/10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
Molding shrinkage, parallel	<b>2.3</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>2.0</b>	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>2250</b>	MPa	ISO 527
Tensile Strength	<b>52</b>	MPa	ISO 527
Nominal strain at break	<b>25</b>	%	ISO 527
Flexural modulus, 23°C	<b>2100</b>	MPa	ISO 178
Flexural strength	<b>73</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>4.7</b>	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>80</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>130</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	<b>130</b>	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Yellow Card available	<b>yes</b>	-	-

Other properties	Value	Unit	Test Standard
Density	<b>1370</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Regional Availability**

Asia Pacific