

DURACON® TW-31

(POM+PE)-MD15

Polyplastics

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	5	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	2.1	%	ISO 294-4, 2577
Molding shrinkage, normal	1.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3750	MPa	ISO 527
Tensile Strength	47	MPa	ISO 527
Strain at break	10	%	ISO 527
Flexural modulus, 23°C	3450	MPa	ISO 178
Flexural strength	81	MPa	ISO 178
Charpy notched impact strength, +23°C	3.3	kJ/m ²	ISO 179/1eA
Rockwell hardness	M 68	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	90	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	100	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	100	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Yellow Card available	yes	-	-

Other properties	Value	Unit	Test Standard
Density	1470	kg/m ³	ISO 1183

Characteristics**Features**

Low Warpage, Tribologic Grade

Regional Availability

Asia Pacific