

ALCOM POM 770/1 PTFE15

(POM+PTFE)

MOCOM Compounds GmbH & Co. KG

Product Texts

Base Polymer	Polyoxymethylene Copolymer
Filler/Additive System	15 % PTFE
Special Features	improved sliding / wear
Market Segment	Automotive, Machinery
Application Area	gear wheels, roller bearings
Typical Applications	functional components, bearings and sliding elements

Processing/Physical Characteristics

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Melt volume-flow rate, MVR	6	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Tensile Modulus	2250	MPa	ISO 527
^[C] Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	4.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
--	-------	------	---------------

ISO Data

^[C] Temp. of deflection under load, 1.80 MPa	90	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	145	°C	ISO 306

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
--	-------	------	---------------

^[C] Density	1480	kg/m ³	ISO 1183
------------------------	------	-------------------	----------

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions in a dry air (dessiccant) dryer 100-110 °C
 for 2-3 h
 in an air circulating dryer 100-110 °C
 for 3-5 h
 dependant on moisture content

Processing Injection Moulding melt temperature 180-220 °C
 mould temperature 60-100 °C

Storage dry, protected from light
 not above 30°C