

LNP™ LUBRICOMP™ Compound KL002

(POM+PTFE)

Saudi Basic Industries Corporation (SABIC)

Product Texts

LNP LUBRICOMP KL002 compound is based on Acetal (POM) Copolymer resin containing 10% PTFE. Added features of this grade include: Wear Resistant.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2550	MPa	ASTM D 638
Tensile Strength at Break	48	MPa	ASTM D 638
Elongation at Break	9.7	%	ASTM D 638
Flexural Modulus	2370	MPa	ASTM D 790
Flexural Strength	68	MPa	ASTM D 790
Izod Impact notched, 1/8 in	53	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	564	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	92	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1450	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	200 - 215	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	175 - 190	°C	-
Zone 2	195 - 205	°C	-
Zone 3	210 - 220	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific