

Product Texts

LNP LUBRICOMP KL004 compound is based on Acetal (POM) Copolymer resin containing 20% PTFE. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E121562-101344623](https://www.ul.com/yellow-card-link/E121562-101344623)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	2.2	%	ISO 294-4, 2577
Molding shrinkage, normal	2.2	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	2.23	mm/mm	ASTM D 955
Mold Shrinkage, TD	2.23	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	47	MPa	ISO 527
Yield strain	10	%	ISO 527
Stress at break	46	MPa	ISO 527
Strain at break	23	%	ISO 527
Flexural modulus	2600	MPa	ISO 178
Flexural strength	79	MPa	ISO 178
Izod impact strength, +23°C, 4mm	45	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	4	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	2130	MPa	ASTM D 638
Tensile Strength at Yield	51	MPa	ASTM D 638
Tensile Strength at Break	50	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Elongation at Break	18	%	ASTM D 638
Flexural Modulus	2060	MPa	ASTM D 790
Flexural Strength	75	MPa	ASTM D 790
Izod Impact notched, 1/8 in	42	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	640	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	98	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB 1.5	class mm	IEC 60695-11-10 -
ASTM Data			
DTUL @ 66 psi	157	°C	ASTM D 648
DTUL @ 264 psi	99	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	0.26	%	Sim. to ISO 62
Density	1500	kg/m ³	ISO 1183
Water Absorption, 24hr	0.15	%	ASTM D 570
Density	1500	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	200 - 215	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	175 - 190	°C	-
Zone 2	195 - 205	°C	-
Zone 3	210 - 220	°C	-

LNP™ LUBRICOMP™ Compound KL004 - Americas

(POM+PTFE)

Saudi Basic Industries Corporation (SABIC)

Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America